
Step	Product	Method	Dry time	Done
Sand		120 → 150 → 180 grit		
Remove dust		Vacuum and tack cloth		
Pre-stain conditioner		Wipe on, wipe off		
Stain coat 1		Wipe on, wipe off excess		
Stain coat 2 (optional)				
Topcoat 1		Thin coat		
Light sand		320 grit		
Topcoat 2–3				